



鍍錫硬銅/鍍錫軟銅絞線 (國家標準 CNS 1367 / CNS 672)

標稱 截面積	構成 條數	計算 斷面積	絞合 外徑	標準 重量	最小 拉斷力 (硬銅線)	最小導體電阻 20°C (Ω / km)		標準 單長
						硬銅線	軟銅線	
mm ²	No./mm	mm ²	mm	kg/km	kg			M
0.9	7/0.4	0.8799	1.2	7.913	—	—	21.1	500
1.25	7/0.45	1.113	1.35	10.02	—	—	16.7	"
1.4	7/0.5	1.375	1.5	12.37	—	—	13.4	"
2.0	7/0.6	1.979	1.8	17.80	—	—	9.28	"
3.5	7/0.8	3.519	2.4	31.66	117	5.28	5.22	"
5.5	7/1.0	5.498	3.0	49.46	183	3.34	3.31	500
8	7/1.2	7.917	3.6	71.19	264	2.32	2.30	"
14	7/1.6	14.08	4.8	126.7	469	1.30	1.29	"
22	7/2.0	21.99	6.0	197.9	713	0.826	0.818	300
30	7/2.3	29.09	6.9	261.7	942	0.625	0.618	"
38	7/2.6	37.16	7.8	334.4	1,200	0.489	0.484	300
50	19/1.8	48.36	9.0	435.1	1,610	0.380	0.376	1,000
60	19/2.0	59.70	10.0	537.0	1,930	0.304	0.301	"
80	19/2.3	78.95	11.5	710.3	2,560	0.230	0.228	"
100	19/2.6	100.9	13.0	907.6	3,270	0.180	0.178	600
125	19/2.9	125.5	14.5	1,129.0	4,070	0.145	0.143	600
150	37/2.3	153.7	16.1	1,390.0	4,980	0.1190	0.118	"
200	37/2.6	196.4	18.2	1,776.0	6,360	0.0930	0.0920	500
250	61/2.3	253.5	20.7	2,298.0	8,210	0.0723	0.0715	300
325	61/2.6	323.8	23.4	2,937.0	10,490	0.0566	0.0560	"
400	61/2.9	402.9	26.1	3,654.0	13,060	0.0455	0.0450	300
500	61/3.2	490.6	28.8	4,448.0	15,890	0.0373	0.0370	"